

IPC15

IP Process™ Clearcoat
with AIR-BAKE™ Technology




- » Sand and buff in 15 minutes at 75° F
- » Dust free in 5 – 7 minutes
- » Energy savings with AIR-BAKE™ Technology
- » Turn off the heat!
- » No flash between coats
- » Speed applications from single to multi-panel repairs
- » Extremely fast cycle times




IPC15


IP Process™ Clearcoat with AIR-BAKE™ Technology




MIXING

 5
IPC15

+

 1
8876


+

 1
TS2, TS3 or TS4



APPLICATION

- Apply 1 double wet coat (No flash between coats).
- 10 psi HVLP/ 29-40 psi Compliant gravity feed
- 1.3 mm = recommended fluid nozzle



DRYING SCHEDULE

Dust Free:

Air Bake™	5-7 minutes @ 75°F
Sand Buff	15-30 minutes @ 75°F

*** 15 minutes = 1.4 – 1.8 mils and 75°F**

**** If higher film builds are utilized,
it will extend the time until you
can sand and buff.**

For more information contact
1-800-526-6704 or visit
www.martinsenour-autopaint.com/ip